

Auramix 300

Advanced low viscosity retarding Superplasticiser, based on Polycarboxylic technology

Uses

Auramix 300 is a high performance retarding superplasticiser intended for applications where retardation and long workability retention are required, and it has been developed for use in:

- Mass raft foundation,
- Pumped concrete,
- Concrete requiring long workability retention,
- High performance concrete.

Advantages

- Increased retardation controls the heat of hydration and yields high ultimate strength
- Arrest bleeding and segregation due to presence of in-built VMA.
- Higher E modulus
- Improved adhesion to reinforcing and prestressing steel
- Better resistance to carbonation
- Lower permeability
- Better resistance to aggressive atmospheric conditions
- Reduced shrinkage and creep
- Increased durability

Standard Compliance

Auramix 300 Complies with IS 9103-1999(2007) . It also complies with ASTM C 494 Type F & Type G depending on the dosage used.

Description

Auramix 300 is a unique combination of the latest generation superplasticisers , based on a polycarboxylic ether polymer with long lateral chains. This greatly improves cement dispersion. At the start of the mixing process an electrostatic dispersion occurs but the cement particle's capacity to separate and disperse. This mechanism considerably reduces the water demand in flowable concrete.

Auramix 300 combines the properties of water reduction and workability retention. It allows the production of high performance concrete and/or concrete with high workability.

Auramix 300 is a strong superplasticiser allowing production of consistent concrete properties around the required dosage.

Technical support

Fosroc provides a technical advisory service for on-site assistance and advice on mix design, admixture selection, evaluation trials and dispensing equipment.

Properties

Appearance	:	Light yellow coloured liquid
pH	:	Minimum 6.0 *
Volumetric mass @ 20° C	:	1.085 kg/litre
Chloride content	:	Nil to IS:456 *
Alkali content	:	Typically less than 1.5 g Na ₂ O equivalent / litre of admixture.

* The uniformity parameters like specific gravity, pH, chloride content etc. will vary for specific customer requirements and mix design. Please refer our MTC issued for specific product configuration for measuring our product parameters that will be constantly and consistently administered.

Dosage

The optimum dosage of Auramix 300 to meet specific requirements should always be determined by trials using the materials and conditions that will be experienced in use. The normal dosage range is between 0.5 to 1.5 ltrs/100 kg of cementitious material.

Use at other dosages

Dosage outside the normal range quoted above can be used to meet particular mix requirements. Contact Fosroc for advice in these cases

Effects of overdosing

Overdosage may cause delay in the setting time and segregation.

Auramix 300

Estimating

Packaging

Auramix 300 is available in 200 kg and 250 kg drums and bulk tanker.

Storage

Auramix 300 has a minimum shelf life of 12 months provided the temperature is kept within the range of 2°C to 50°C. Should the temperature of the product fall outside this range then contact local Fosroc office for advice.

Precautions

Health and safety instructions

Auramix 300 does not fall into the hazard classifications of current regulations. However, it should not be swallowed or allowed to come into contact with skin and eyes.

Suitable protective gloves and goggles should be worn.

Splashes on the skin should be removed with water. In case of contact with eyes rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately - do not induce vomiting.

For further information refer the Safety Data sheet available for this product.

Fire

Auramix 300 is water based and non-flammable.

Cleaning and disposal

Spillages of Auramix 300 should be absorbed onto sand, earth or vermiculite and transferred to suitable containers. Remnants should be hosed down with large quantities of water.

The disposal of excess or waste material should be carried out in accordance with local legislation under the guidance of the local waste regulatory authority.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

Embassy Point, No. 150,
2nd Floor, Infantry Road,
Bangalore 560 001,
Karnataka

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

+91 80-42521900

fax

+91 80-22281510

e-mail

enquiryindia@fosroc.com

Regional Offices

Chennai

Hills Centre, Old No. 5,
New No. 9, 3rd Cross Street,
Jeth Nagar, Raja Annamalaiapuram,
Chennai 600 028.
Ph: +91 44 61304500

Mumbai

MBC Park, 12th floor, Office No. 12B,
'D' Block, Near G Corp/Hyper City
Kasarwadawali, Ghodbunder Road,
Thane (West) 400 615
Ph: +91 22 6229 6800
Fax: 022 62296809

Noida

Unit No. 601, Highway Tower-II
A-13/2, 6th Floor, Sector-62
Gautam Buddha Nagar,
Noida 201 309, Uttar Pradesh
Ph: +91 120 6121900
Fax: 0120-4270622

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph: +91 33-65343188
Fax: 033-2499-0280