

Nitomortar 30

Chemical and abrasion resistant epoxy repair compound.

Uses

For permanent repairs to concrete structure and cementitious substrates where strength, impermeability to water and resistance to aggressive chemicals is required. Ideally suited for maintaining engineering, chemical handling and processing plants.

Advantages

- **Chemical Resistance** : Unaffected by wide range of acids, alkalis and industrial chemicals
- **Easily applied** : Designed for easy application to a fair finish
- **Quality** : Pre-weighed quality controlled materials ensure consistency and reduce risk of site errors
- **Proven performance** : Successful use proves for a wide variety of aggressive applications

Description

Nitomortar 30 is a three part solvent free combination of epoxy resin, modified amine hardeners filled with specially graded chemically inert aggregates with high crushing strength.

It is applied by trowel as a durable chemical resistant repair mortar 3-6 mm thick depending upon the requirement. The system includes Nitoprime 25 a two part epoxy resin primer and Nitomortar 30 which are both supplied in preweighed units ready for onsite mixing and application. The finished area has a slightly granular texture of uniform self colour. However, as the natural grade takes its colour from the aggregates which is subjected to variation, colour matching is not practicable with this grade.

Technical Support

Fosroc offers a technical support package to specifiers, end users and contractors as well as onsite technical assistance all over the country.

Properties

Curing characteristics at 30°C

Nitomortar 30

Pot life : 30 min.

Initial hardness : 16 hrs

Full cure : 7 days

Mechanical characteristics @ full cure

Compressive strength : 45 N/mm²

Flexural strength : 12 N/mm²

Tensile strength : 4.5 N/mm²

Bond strength to concrete : 3.0 N/mm²

Nitoprime 25

Pot life : 30 min. @ 30°C

Maximum overlay time : 30 min. @ 30°C

Chemical Resistance

Acids

Hydrochloric 10%	Excellent
Sulphuric 10%	Excellent
Phosphoric 30%	Excellent
Nitric 10%	Good
Lactic 10%	Excellent
Citric 10%	Excellent

Alkalis

Sodium Hydroxide 30%	Excellent
Ammonia 10%	Excellent

Organic Solvents

Butanol	Good
White Spirit	Excellent
Oil/Grease/Petrol	Excellent
Xylene	Good
Acetone	Not resistant
Skydrol	Good
Sat. Sugar	Excellent

Aqueous solutions

Conc. Bleach	Excellent
Sat. Urea	Excellent

Those materials marked 'Good' are suitable for areas of occasional spillage where good housekeeping is in force.

All the above properties have been determined by laboratory controlled tests and are typical of those expected in practice.

Nitomortar 30

Estimating

Packaging and Coverage

	Pack size	Approx. Coverage rate
Nitoprime 25	1 & 4 litres	5.5 - 6.5 m ² /litre
Nitomortar 30	8 litres	2.67m ² @ 3mm thickness/pack 1.33m ² @ 6mm thickness/pack

The coverage rates are given for guidance only as actual quantities used will vary on nature of substrate and conditions on site.

Storage

Shelf life

Nitoprime 25 and Nitomortar 30 have a shelf life of 12 months if stored in unopened containers below 35°C.

Precautions

Health and safety instructions

Nitozinc Primer, Nitoprime 25 and Nitomortar 30 should not come in contact with skin or eyes, or be swallowed. Adequate ventilation shall be provided and inhalation of vapours shall be avoided. Some people are sensitive to resins, hardeners and solvents. Suitable protective clothing, gloves and eye protection shall be worn. If working in confined areas, suitable respiratory protective equipment must be used. The use of barrier creams provide additional skin protection.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

Embassy Point, No. 150,
2nd Floor, Infantry Road,
Bangalore 560 001,
Karnataka

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

+91 80-42521900

fax

+91 80-22281510

e-mail

enquiry.india@fosroc.com

In case of contact with skin, it shall be removed immediately with resin removing cream followed by washing with soap and water. Solvent should not be used. In case of contact with eyes, it shall be rinsed immediately with plenty of clean water and medical advice shall be sought. If swallowed, medical attention shall be sought immediately - Vomiting should not be used.

For further information, refer the Safety Data sheet available for this product.

Fire

Nitomortar S mortar is nonflammable.

Nitozinc Primer and Nitoprime 25 are flammable. It shall be kept away from sources of ignition. Smoking is prohibited during handling / application of the product. In the event of fire, use of fire extinguishers like carbon-dioxide or foam is suggested. Use of water jet is not suggested.

Flash points

Nitozinc Primer 16°C

Nitoprime 25 25°C

Additional information

Fosroc manufactures a wide range of products specially designed for the repair and refurbishment of damaged reinforced concrete. This includes hand placed and spray grade repair mortars, fluid microconcretes, chemical resistant epoxy mortars and a comprehensive package of protective coatings. In addition, a wide range of complementary products are available.

Regional Offices

Chennai

Hills Centre, Old No 5,
New No 9, 3rd Cross Street,
Jeth Nagar, Raja Annamalaipuram,
Chennai 600 028.
Ph: 9500064795

Mumbai

MBC Park, 12th floor, Office No.12B,
'D' Block, Near G Corp/Hyper City
Kasarwadawali, Ghodbunder Road,
Thane (West) 400 615
Ph: +91 22 6229 6800

Noida

Unit No. 601, Highway Tower-II
A-13/2, 6th Floor, Sector- 62
Gautam Buddha Nagar,
Noida 201 309, Uttar Pradesh
Ph: +91 120 6121900
Fax: 0120-4270622

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph: +91 33-65343188
Fax: 033-2499-0278